



## SERIES 2000 "K" POLYMERIC DISPERSIONS FOR AQUEOUS SYSTEMS

**SERIES 2000 K DISPERSIONS** are liquid pigment dispersion concentrates for tinting and masstone applications.

**VEHICLE:** K Dispersions are made with a unique proprietary polymeric vehicle. This technology allows us to produce dispersions with vehicle solids at 1.0 % to 6.0 % max. and propylene glycol levels 3.0 % to 5.0 % max.

**SOLVENT:** Propylene Glycol

K DISPERSIONS offer formulators an alternative. These colorants do not contain surfactants.

K Dispersions contain only prime pigments. Inexpensive fillers are not used to boost pigment loads.

K Dispersions will not adversely effect gloss or water sensitivity. Due to the small amount of Glycol, dry times should remain acceptable.

K Dispersions have excellent compatibility and exhibit excellent color acceptance in most aqueous systems.

### TECHNICAL DATA

CODE	DESCRIPTION	COLOR INDEX	WT/GAL, LBS	SPECIFIC GRAVITY	PIGMENT	% BY WEIGHT		% BY VOLUME			VOC	
						VEHICLE SOLIDS	VOLATILES	PIGMENT	VEHICLE SOLIDS	VOLATILES	LBS/GAL	G/L
K 106	WHITE	WH6	17.26	2.07	74.2	1.2	24.60	42.5	1.7	55.80	1.26	151
K 342	YELLOW OXIDE	Y42	15.51	1.86	60.0	2.5	37.50	28.0	2.7	69.30	1.46	173
K 365	HANSA YELLOW (RS)	Y65	9.66	1.16	30.0	3.6	66.40	19.8	3.2	77.00	1.69	202
K 374	HS HANSA YELLOW	Y74	9.72	1.17	35.0	4.7	60.30	26.7	3.2	70.10	1.32	157
K 383	ORGANIC YELLOW (RS)	Y83	9.40	1.13	30.0	4.2	65.80	22.4	3.3	74.30	1.5	179
K 3151	ORGANIC YELLOW (GS)	Y151	9.48	1.13	30.0	4.2	65.80	21.7	3.4	74.90	1.54	184
K 434	DIARYLIDE ORANGE	O34	9.86	1.18	40.0	3.5	56.50	30.5	3.2	66.30	1.28	112
K 5101	RED OXIDE LIGHT	R101	16.47	1.98	60.0	1.5	38.50	23.0	1.7	75.30	1.72	206
K 5102	RED OXIDE MEDIUM	R101	16.47	1.98	60.0	1.5	38.50	23.0	1.7	75.30	1.72	206
K 5112	PERMANENT RED	R112	9.46	1.14	35.0	4.7	60.30	28.2	3.4	68.40	0.97	117
K 5172	LIGHT ORGANIC RED	R170	9.11	1.09	30.0	2.6	67.40	24.5	2.2	73.30	1.40	171
K 5175	DEEP ORGANIC RED	R170	9.11	1.09	30.0	2.6	67.40	24.3	2.2	73.50	1.44	173
K 67	PHHALO GREEN	GR7	9.99	1.20	30.0	5.6	64.40	17.7	5.2	77.10	1.74	208
K 8152	PHHALO BLUE (RS)	B15.2	9.40	1.13	30.0	3.3	66.70	22.2	2.8	75.00	1.53	183
K 8154	PHHALO BLUE (GS)	B15.4	9.49	1.14	30.0	3.3	66.70	21.4	2.9	75.70	1.58	199
K711	BURNT UMBER	BR7	11.92	1.43	40.0	2.8	57.20	15.6	6.1	78.30	2.13	256
K97	BLACK	BK7	9.59	1.15	35.0	3.8	61.20	23.0	1.6	75.40	1.55	182