



SERIES 2000 "HP"

HIGH PERFORMANCE ACRYLIC DISPERSIONS

SERIES 2000 HP DISPERSIONS are liquid pigment dispersion concentrates for tinting and masstone applications. HP Dispersions are compatible with most high performance solventborne systems. All pigments used in HP Dispersions exhibit lightfastness, heat resistance and bleed resistance properties.

VEHICLE: Modified thermoplastic acrylic

SOLVENT: Blend of PM Acetate and Aromatic 100

TECHNICAL DATA

CODE	DESCRIPTION	COLOR INDEX	WT/GAL, LBS	SPECIFIC GRAVITY	PIGMENT	% BY WEIGHT			% BY VOLUME			VOC	
						VEHICLE SOLIDS	VOLATILES	PIGMENT	VEHICLE SOLIDS	VOLATILES	LBS/GAL	G/L	
HP 3106	NON-CHALKING TiO2	WH6	15.82	1.92	65.0	15.0	20.0	31.3	26.7	42.0	3.21	384	
HP 3350	TRANSPARENT YELLOW OXIDE	Y42	10.41	1.25	35.0	30.0	35.0	9.0	29.9	61.1	4.68	578	
HP 33139	ORGANIC YELLOW (RS)	Y83	8.62	1.03	20.0	21.7	58.3	11.3	22.3	66.4	5.10	612	
HP 33151	LIGHT ORGANIC YELLOW	Y151	8.74	1.05	26.0	20.3	53.7	17.5	20.8	61.7	4.58	561	
HP 3342	LT. LEMON YELLOW OXIDE	Y42	13.84	1.66	55.0	20.0	25.0	22.8	31.2	46.0	3.43	412	
HP 3434	DIARYLIDE ORANGE	OR34	8.70	1.05	22.0	30.0	48.0	16.4	27.3	56.3	4.20	501	
HP 3550	TRANSPARENT RED OXIDE	R101	10.41	1.26	35.0	30.0	35.0	8.30	31.0	60.7	4.68	542	
HP 35101	RED OXIDE LIGHT	R101	14.93	1.79	56.0	20.6	23.4	19.5	34.3	46.2	3.50	420	
HP 35103	RED OXIDE DARK	R101	15.90	1.91	60.0	22.0	18.0	22.2	39.2	38.6	2.86	343	
HP 35172	LIGHT ORGANIC RED	R170	8.56	1.03	22.0	31.6	46.4	16.0	30.3	53.7	3.99	478	
HP 35175	DEEP ORGANIC RED	R170	8.29	0.96	20.0	22.3	57.7	14.7	20.7	64.6	4.79	575	
HP 3519	QUINACRIDONE RED	V19	8.42	1.01	19.0	19.6	61.4	13.3	16.9	69.8	5.17	621	
HP 35522	BON MAROON	R52.2	8.63	1.04	23.0	26.2	50.8	17.0	25.3	57.7	4.37	524	
HP 3636	PHTHALO GREEN (YS)	GR36	9.53	1.14	24.0	27.5	48.5	9.3	29.2	61.5	4.63	551	
HP 367	PHTHALO GREEN	GR7	9.10	1.09	23.0	26.4	50.6	12.4	26.8	60.8	4.60	551	
HP 3700	RAW UMBER	BR7	13.40	1.60	55.0	20.8	24.2	24.6	31.3	44.1	3.26	391	
HP 3711	BURNT UMBER	BR7	13.02	1.56	51.0	24.6	24.4	21.9	35.5	42.6	3.15	377	
HP 3722	VAN DYKE BROWN		11.38	1.36	42.0	17.7	40.3	15.7	22.5	61.8	4.59	551	
HP 3800	PHTHALO BLUE NFNC	B15.2	8.67	1.04	22.0	24.2	53.8	14.9	22.2	62.9	4.66	559	
HP 38152	PHTHALO BLUE (RS)	B15.2	8.58	1.03	21.0	24.4	54.6	14.2	22.5	63.3	4.68	561	
HP 38154	PHTHALO BLUE (GS)	B15.4	8.89	1.07	22.0	33.0	45.0	14.5	33.1	52.4	3.99	478	
HP 3819	QUINACRIDONE VIOLET	V19	8.26	0.99	12.0	26.2	61.8	8.0	22.1	69.9	5.10	612	
HP 3823	CARBAZOLE VIOLET	V23	8.16	0.98	10.0	22.0	68.0	6.6	18.2	75.2	5.60	666	
HP 3900M	HIGH JET. MASSTONE BLACK	BK7	8.64	1.04	18.0	35.0	47.0	10.0	21.0	69.0	3.90	467	
HP 3955M	MASSTONE BLACK	BLK7	8.89	1.07	22.0	33.0	45.0	13.0	32.1	54.9	4.00	480	
HP 397T	TINTING BLACK	BK7	9.60	1.15	28.0	30.0	42.0	17.8	27.4	54.8	4.02	481	