



# Flatting Pastes: EZ FLAT 20 BA

Flatting Agent for Solvent-Based Applications

**EZ FLAT 20 BA** is a matting/flatting paste for systems in which Butyl Acetate is the preferred solvent such as lacquers and bake finishes.

**Suggested Incorporating Techniques:** EZ FLAT 20 BA should always be mixed prior to use. In most cases the EZ FLAT 20 BA will be more viscous than the systems in which it will be used. Because of this we recommend pre-mixing EZ FLAT 20 BA first by diluting it with 5 to 10% solvent to be comparable with the viscosity of the system for incorporation, then added slowly into the batch while it is under agitation.

**Typical Usage Levels:** Add 5% by weight, to reduce gloss 70% at 60°F. System solids and force cure vs. ambient will effect actual level required. For consistent results, agitate lightly before using (based on 35% vehicle solids).

## Typical Properties:

Percentage Silica	15%
Percentage Vehicle	0%
Percentage Solvent	85% n Butyl Acetate
Weight per Gallon (lbs)	8.04
Specific Gravity	0.96
Flash Point F/C (closed cup)	83°/28°