



# Flatting Pastes: EZ FLAT A-100

Flatting Agent for Solvent-Based Applications

**EZ FLAT A-100** is a matting/flatting paste for systems which Aromatic 100 is the preferred solvent such as lacquers and bake finishes.

**Suggested Incorporating Techniques:** EZ FLAT should always be mixed prior to use. In most cases, the EZ FLAT will be more viscous than the systems in which it will be used. Because of this, we recommend pre-mixing EZ FLAT first by diluting it with 5 to 10% solvent to be comparable with the viscosity of the system for incorporation, then added slowly into the batch while it is under agitation.

**Typical Usage Levels:** Add 5% by weight, to reduce gloss 70% at 60°F. System solids and force cure vs. ambient will effect actual level required. For consistent results, agitate lightly before using (based on 35% vehicle solids).

## Typical Properties:

Percentage Silica	15%
Percentage Vehicle	0%
Percentage Solvent	85% Aromatic 100
Weight per Gallon (lbs)	7.84
Specific Gravity	0.94
Flash Point F/C (closed cup)	110°/43°