



PIGMENT DISPERSIONS: RD

STANDARD COLORANTS (1/2)

RD DISPERSIONS are pourable, solvent-free, easy to incorporate liquid pigment dispersion concentrates for tinting and masstone applications. They are designed for optimum performance and ease of use in epoxy, polyaspartic and other 2K systems. **RD DISPERSIONS** have little effect on gloss, dry time and resistance properties. All pigments used in **RD DISPERSIONS** exhibit lightfastness and contain no inert fillers.

Vehicle: Proprietary Polyester

Technical Data:

Code	Description	Color Index	Wt/Gal,Lbs	Specific Gravity	Percentage by Weight			Percentage by Volume			VOC	
					Pigment	Vehicle Solids	Volatiles	Pigment	Vehicle Solids	Volatiles	Lbs/Gal	G/L
RD 6106	WHITE RUTILE TiO ₂	WH6	14.84	1.78	60.0	38.4	0	26.7	71.9	0	0.0056	0.67
RD 6107	HIGH STRENGHT WHITE	WH6	19.78	2.37	78.0	22.0	0	46.3	53.7	0	0.0039	0.47
RD 63184	BISMUTH VANADATE	Y184	21.81	2.62	75.0	24.4	0	32.7	66.4	0	0.0049	0.59
RD 6342	LIGHT LEMON YELLOW OXIDE	Y42	13.49	1.62	50.0	45.6	0	19.7	76.6	0	0.0056	0.67
RD 6374	ORGANIC YELLOW	Y74	8.70	1.04	25.0	75.0	0	18.6	81.4	0	0.0060	0.72
RD 6383	ORGANIC YELLOW (RS)	Y83	8.65	1.04	20.0	80.0	0	13.7	86.3	0	0.0064	0.77
RD 6434	DIARYLIDE ORANGE	OR34	8.73	1.05	25.0	75.0	0	18.3	81.7	0	0.0064	0.72
RD 65102	RED IRON OXIDE MEDIUM	R101	13.84	1.66	50.0	45.2	0	17.1	78.2	0	0.0058	0.70
RD 65103	RED IRON OXIDE DARK	R101	13.94	1.67	50.0	45.2	0	17.1	78.7	0	0.0059	0.71
RD 65254	DPP RED	R254	9.25	1.11	35.0	65.0	0	30.5	74.8	0	0.0055	0.64
RD 6607	PHTHALO GREEN	GR36	8.84	1.06	18.0	82.0	0	9.4	90.6	0	0.0068	0.82
RD 6617	GREEN OXIDE	GR7	14.08	1.69	50.0	45.2	0	16.3	79.5	0	0.0059	0.71
RD 68152	PHTHALO BLUE (RS)	B15.2	8.63	1.04	18.0	82.0	0	11.8	88.2	0	0.0065	0.78
RD 68154	PHTHALO BLUE (GS)	B15.4	8.90	1.07	18.0	77.0	0	11.5	85.7	0	0.0064	0.77
RD 6819	QUINACRIDONE VIOLET	V19	8.47	1.02	15.0	85.0	0	10.2	89.8	0	0.0066	0.79
RD 6900M	MASSTONE BLACK	BK7	8.67	1.04	15.0	83.7	0	8.7	90.6	0	0.0067	0.81
RD 6097T	TINTING BLACK	BK7	8.83	1.06	15.0	80.0	0	8.8	91.2	0	0.0067	0.80