



PIGMENT DISPERSIONS: XVOG

HIGH-PERFORMANCE LOW VOC DISPERSIONS FOR SOLVENTBORNE SYSTEMS

XVOG DISPERSIONS are liquid pigment dispersion concentrates for tinting and masstone applications. They are **LOW VOC** and compatible with most solventborne systems. All pigments used in **XVOG DISPERSIONS** exhibit lightfastness, heat resistance and bleed resistance properties.

Vehicle: Modified Aldehyde **Solvent:** Oxsol 100

Technical Data:

Code	Description	Color Index	Wt/Gal,Lbs	Specific Gravity	Percentage by Weight			Percentage by Volume			Lbs/Gal	VOC G/L
					Pigment	Vehicle Solids	Volatiles	Pigment	Vehicle Solids	Volatiles		
XVOG 0106	Titanium White	WH6	16.73	2.01	55.6	17.9	26.5	27.9	32.5	39.6	0.031	3.68
XVOG 0300	Transparent Yellow Oxide	Y42	13.05	1.57	29.4	18.4	52.2	12.9	26.2	60.9	0.035	4.24
XVOG 0315183	L/F Medium Yellow	Y83	10.96	1.32	36.0	28.0	36.0	30.6	34.1	35.3	0.022	2.64
XVOG 03175	Organic Yellow G/S	Y175	10.93	1.31	30.6	24.0	45.4	26.4	29.2	44.4	0.026	3.08
XVOG 0342	Yellow Iron Oxide	Y42	16.71	2.01	53.8	13.69	32.5	26.3	25.8	47.9	0.039	4.66
XVOG 043436	L/F Orange	OR34	10.90	1.31	26.3	22.3	51.4	23.0	26.9	50.1	0.029	3.44
XVOG 0500	Transparent Red Oxide	R101	12.78	1.53	22.5	13.5	64.0	8.0	18.9	73.1	0.051	6.14
XVOG 05102	Red Oxide Light	R101	17.63	2.12	59.5	12.7	27.8	15.2	25.8	59.0	0.041	4.88
XVOG 05173	Mono Azo Red	R173	10.88	1.31	30.0	20.6	49.4	27.2	24.8	48.0	0.026	3.07
XVOG 0519	Quinacridone Red	V19	10.66	1.28	17.7	28.3	54.0	15.4	33.1	51.5	0.031	3.76
XVOG 05522	Bon Maroon	R52.2	10.63	1.28	12.4	34.2	53.4	9.5	39.8	50.7	0.027	3.22
XVOG 067	Phthalo Green	GR7	11.10	1.33	20.0	36.0	44.0	12.5	43.8	43.7	0.025	2.94
XVOG 0700	Raw Umber	BR7	13.46	1.62	38.5	22.1	39.4	19.1	33.5	47.4	0.027	3.23
XVOG 0711	Burnt Umber	BR7	14.34	1.72	46.3	23.3	30.4	24.0	36.7	39.3	0.115	13.74
XVOG 0815254	Phthalo Blue	B15.2	10.85	1.30	24.8	29.7	45.5	20.0	38.8	41.2	0.026	3.14
XVOG 0819	Quinacridone Violet	V19	10.67	1.28	20.1	29.9	50.0	17.3	35	47.7	0.025	3.01
XVOG 0900	Jet Black	BK7	10.69	1.28	9.5	31.1	59.4	6.8	36.5	56.7	0.032	3.80
XVOG 097	Lamp Black	BK7	11.02	1.32	17.8	28.1	54.1	13.1	33.7	53.2	0.029	3.44

Eagle Specialty Products · 2216 North Broadway · St. Louis, MO 63102
 (314) 241-7771 · (888) 241-9802 · Fax: (314) 241-5356
www.espinc.us

Our data is based on laboratory tests which are believed to be accurate. However, all recommendations are made without warranty since the conditions of use are beyond the control of Eagle Specialty Products. We do not assume any liability of the product relative to performance or injury resulting from its use. Liability, if any, is limited to replacement product.